

(19) World Intellectual Property Organization  
International Bureau



(43) International Publication Date  
9 October 2003 (09.10.2003)

PCT

(10) International Publication Number  
**WO 03/082733 A2**

(51) International Patent Classification<sup>7</sup>: **B82B 3/00**,  
C01B 31/02, D01F 9/12

(21) International Application Number: **PCT/NZ02/00055**

(22) International Filing Date: **3 April 2002 (03.04.2002)**

(25) Filing Language: **English**

(26) Publication Language: **English**

(71) Applicant (for all designated States except US): **CANTERPRISE LTD.** [NZ/NZ]; University of Canterbury,  
P.O. Box 4800, Christchurch (NZ).

(81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZM, ZW.

(84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

(72) Inventor; and

(75) Inventor/Applicant (for US only): **ABRAHAMSON, John** [NZ/NZ]; 16a de Thier Lane, Christchurch (NZ).


Published:

— without international search report and to be republished upon receipt of that report

(74) Agents: **WEST-WALKER, Gregory, J. et al.**; A J Park, 6th Floor Huddart Parker Building, 1 Post Office Square, Post Office Square, PO Box 949, Wellington 6015 (NZ).

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: **CONTINUOUS METHOD FOR PRODUCING INORGANIC NANOTUBES**



(57) Abstract: Production of nanotubes of carbon or of other inorganic material by moving a carbon-containing substrate (8), such as a tape or belt of carbon fibres, within a reaction chamber (1) either through an electric arc in a gap between two electrodes (2, 3) or adjacent an electrode so that an electric arc exists between the electrode and the substrate, to cause the nanotubes to form on the substrate (8). The method enables the continuous or semi-continuous production of nanotubes. Preferably, the process is carried out at atmospheric pressure and nanotubes of high purity are produced.

WO 03/082733 A2